TEST REPORT

LAB NO.: (6621)235-0050
FORM NO.: /
DATE IN: Aug 23, 2021
DATE OUT: Aug 26, 2021
NO. OF WORKING DAYS: 4
PAGE 1 OF 3

OVERALL RATING

PASS	X
FAIL	
DATA	

Vendor:	WUHAN YOUFU INTERNATIONAL TRADE CO LTD	**Agent:**	/
Fabric Supplier/Mill:	/	**Factory/Manufacturer:**	/
P.O. No.:	/	**Style No.:**	/
Sample Description:	AAMI LEVEL 2 MICROPOPOUS COVERALL/AAMI LEVEL 3 MICROPOPOUS COVERALL	**Style Description:**	/
Color:	/	**Country of Origin:**	/
Claimed Fabric Weight:	/	**Claimed Fabric Count:**	/
Yarn Size:	/	**Submitted Size:**	/
Size Range:	/	**FPU No.:**	/
GPU No.:	/	**End Use:**	/
SKU:	/		

Product Category	/
Test Requested	PARTIAL TEST
Previous Report No.	/

Submitted Fiber Content	/
Actual Fiber Content	/
Suggested Fiber Content	/
Submitted Care Instruction(s)	/
Client Expected Care Instruction	/
Suggested Care Instruction(s)	/

TEST PROPERTY	PASS	FAIL	DATA	COMMENTS
WATER RESISTANCE: IMPACT PENETRATION TEST	X			
WATER RESISTANCE: HYDROSTATIC PRESSURE TEST	X			

Bvcps (Shanghai) Contact Information For This Report

General Information:

Challenge Qiao   Tel: 086-021-24081666*9331, email: challenge.qiao@bureauveritas.com

Pat Liu   Tel: 086-021-24081745, email: pat.liu@bureauveritas.com

Technical Questions:

Carrie Cao   Tel: 86-21-24081943, email: carrie.cao@bureauveritas.com

BUREAU VERITAS
CONSUMER PRODUCTS SERVICES (SHANGHAI)

CARRIE CAO
PROGRAM MANAGER

C/N SM/MICK

TEST RESULTS

TEST PROPERTY					REQUIREMENTS

WATER RESISTANCE: IMPACT PENETRATION TEST (AATCC 42-17)

AS RECEIVED (G.)

FABRIC	0.0				MAX. 1.0 G.
SLEEVE	0.0				MAX. 1.0 G.
BACK	0.0				MAX. 1.0 G.
INSIDE	0.0				MAX. 1.0 G.

WATER RESISTANCE: HYDROSTATIC PRESSURE TEST (AATCC 127, OPTION 2, HYDROSTATIC HEAD TESTER AT 60 MBAR/MIN, DISTILLED OR DEIONIZED WATER AT 21+/-2 DEGREE CELSIUS)

	1	2	3	AVE	
FABRIC	>50	>50	>50	>50	MIN. 50CM H_2O
HOOD				>50	MIN. 50CM H_2O
SLEEVE				>50	MIN. 50CM H_2O
BACK				>50	MIN. 50CM H_2O
INSIDE				>50	MIN. 50CM H_2O

Report Number
(6621)235-0050

END OF REPORT

C/N SM/MICK